



papergraphics

THE LARGE-FORMAT PRINT SPECIALIST

DF/DFL1 | Digiflör® Tactile fire-rated slip-rated cushioned vinyl flooring 1000gsm

Product Code: DF/DFL1



Available options

- DF/DFL1 | Digiflör® Tactile fire-rated slip-rated cushioned vinyl flooring 1000gsm - 1600mm x 20m (1 Roll Box)
- DF/DFL1 | Digiflör® Tactile fire-rated slip-rated cushioned vinyl flooring 1000gsm - 2050mm x 30m (1 Roll Box)
- DF/DFL1 | Digiflör® Tactile fire-rated slip-rated cushioned vinyl flooring 1000gsm - 2200mm x 20m (1 Roll Box)
- DF/DFL1 | Digiflör® Tactile fire-rated slip-rated cushioned vinyl flooring 1000gsm - 2200mm x 30m (1 Roll Box)
- DF/DFL1 | Digiflör® Tactile fire-rated slip-rated cushioned vinyl flooring 1000gsm - 3200mm x 20m (1 Roll Box)

We're truly proud of Digiflör Tactile - our new durable cushioned flooring that has been devised especially for printed flooring installations. Digiflör Tactile not only gives superb print quality but also offers a high level of durability. This premium new product is fully fire-rated, and has shown strong results in the Pedatron durability test too, ensuring that it is the perfect choice for exhibitions, events and any place that requires a safe, sumptuous and perfectly-printable flooring.

Our foot-friendly cushioned flooring adds another level of quality to interior spaces; utilising a fully printable surface to provide a truly premium flooring experience. Perfect for exhibitions, POS, retail spaces and much more.

Product Features

- EN 13501 fire rating for added safety
- Fully printable - bring your clients' ideas to life!
- Ink receptive top coating to aid durability

•	Woven middle layer for increased tensile strength
•	R11 Ramp Test slip rated
•	Ideal for indoor spaces with low-to-medium traffic

Product Properties	
Brand	PG Digiflor
Colour	N/A
Media weight (gsm)	1000
Media thickness (micron)	2000
Core diameter	76mm
Tensile strength warp	1500 N/5cm DIN 53354 BS 3424 Method 6A
Tensile strength weft	800 N/5cm DIN 53354 BS 3424 Method 6A
Tear strength warp	50 N DIN 53356 BS 3424 Method 7A
Tear strength weft	35 N DIN 53356 BS 3424 Method 7A
Usage temperature	-20c to 70c
Construction	Polyester and PVC, with ink-receptive top coating

Ink Technology Compatibility	
Use with Aqueous Dye inks:	Not Recommended
Use with Aqueous Pigmented inks:	Not Recommended
Use with Oil Pigmented inks:	Not Recommended
Use with Laser toner:	Not Recommended
Use with Latex inks:	Recommended
Use with Solvent inks:	Not Recommended
Use with Eco-Solvent inks:	Not Recommended
Use with UV Curable inks:	Recommended
Use with Dye-Sublimation inks:	Not Recommended
Compatability notes	Suitable for use on printers that can accommodate at least 2.2mm product thickness. For roll fed machines; please check that the machine can take the weight of the roll. (1600mm x 20m = 33kgs, 2200mm x 20m = 45kgs and the 3200mm x 20m = 65kgs). Please note, for Latex printing this product is only compatible with HP Latex 1500, 2700, 3000, 3100, 3200, 35000, 3600, R1000, and R2000 printers.

Product Certifications	
•	Slip rating - BS 7976-2: 2002 Pendulum Test
•	Fire rating - EN 13501-1: Bfl-s1
•	Slip rating - DIN 51130 - R11
•	Pedatron Test - SATRA STM 528
•	RoHS compliant

Usage Guidance

- Digiflor can be laid on any hard, smooth surface such as hardboard, wood, concrete or stage decking and can be cleaned by using a diluted non-chlorine detergent
- The lifetime of this product depends on location and the amount of foot traffic, however it's typically designed to last at least six months under light to medium traffic.
- To ensure consistency when using Digiflör, we recommend printing rolls from the same batch, as well as consecutive rolls numbers. Don't hesitate to get in touch for more information.

Tel: +44 (0) 345 1300 772

Email: info@paper-graphics.com

Papergraphics



Diva Innovation Centre Crompton Way, Crawley West Sussex RH10 9QR

© Papergraphics 2025 | Registered Number: 01726045. VAT number: GB644666414.