DigiDot Matt White.

Technical Data Sheet

Material	Monomeric calendered PVC		
Colour & Finish	Matt white, embossed		
Stock Width	1370mm		
Weight	130gsm ±10gsm	ASTM D 1593	
Thickness	100 µ ±10 µ	ASTM D 1593	
Opacity	98.88% (blockout)		
Gloss (60°)	≤ 15%	ASTM D 523	
Fire Rating	B-s1, d0	ISO 13501-1 / ISO 11925-2	
Adhesive	Type	Acrylic removable, clear	
	Pattern	Dot matrix, easy apply	
	Min. Appl. Temp.	+10°C	
	Service Temp.	-10°C/+70°C	
	Peel Adhesion 20 min	> 2 N/25mm	FINAT FTM1
	Peel Adhesion 24 hr	> 4 N/25mm	FINAT FTM1
	Dimensional Stability	Max. 0.5mm	FINAT FTM14
Liner	Type	Double sided PE	
	Weight	135 gsm ±10%	ISO 536
	Thickness	148 µ ±10 µ	ISO 534
Durability	Indoor up to 12 months / Outdoor up to 3 months		
Shelf Life	24 months unprocessed, stored at 20°C ±5°C and 50% ±5% RH, upright in the original packaging, away from direct sunlight and heat.		
Printing	Solvent, latex, UV and UV gel. Latex printing at a maximum of 105°C. Avoid excessive ink coverage. Allow 48 hours drying, unrolled, before any further finishing.		
Applications	Short term indoor graphics on smooth surfaces, with easy application, repositioning and removal. Not recommended for wet application, lamination, floor graphics, drywall, plaster, wallpaper, or rough, flexible or low-energy surfaces. Acclimatise for 24 hours and clean surfaces thoroughly before application. Remove slowly (max. 5cm per second). Allow hot surfaces such as shop windows to cool before removal. Testing between substrate and adhesive recommended prior to use.		

DPM
DIGITAL PRINT MEDIA

T: 01494 760240 **E:** sales@dpm.com **W:** www.dpm.com

DPM, Digital Print Media & Frieze Frames are trading names of Roseash Ltd. Registered in England 2920080, VAT GB 645 5703 29
Roseash Limited, Unit B The Height Business Centre, Ibstone Road, Stokenchurch, Buckinghamshire, HP14 3BG