

Technical Data Sheet



Vision Lycra

Material	91% Polyester 9% Elastan			
Stock widths	310cm			
Weight				
acc. to DIN EN 12127	230.00	[g/m ²]	+ - 3	[%]
Tearing strength				
Maximum tensile elongation, longitudinal direction				
acc. to DIN EN ISO 13934-1	135.00	[%]	+ - 20	[%]
Maximum tensile elongation, cross direction				
acc. to DIN EN ISO 13934-1	135.00	[%]	+ - 20	[%]
Maximum tearing strength, longitudinal direction				
acc. to DIN EN ISO 13934-1	min. 640.00	[N/5 cm]		
Maximum tearing strength, cross direction				
acc. to DIN EN ISO 13934-1	min. 640.00	[N/5 cm]		
Flame retardancy	B1 / EN13501			



Roseash Limited, Unit B The Height Business Centre, Ibstone Road, Stokenchurch, Buckinghamshire, HP14 3BG
T: 01494 760240 E : sales@dpm.com W : www.dpm.com