

Technical Data Sheet



Vision 440gsm Coated Frontlit B1

Material	Coated PVC	
Stock widths	160cm / 250cm / 320 cm / 500cm	
Weight		
DIN EN ISO 2286-2	440	[g/m ²]
Transmittance		
ASTM E 424 6.5.2	9.5	% / mm/s
Tensile Strength		
ISO 13934 2-2000 CRE cut strip method	L:263.4 W:263	KGf/5C
Tearing Strength		
ISO 13937-2:2000 CRE single tear method	L:34.5 W:30.2	KGf
Elongation		
ISO 13934-2:2000 CRE cut strip method	L:30.9 W:30.5	%
Adhesion Strength		
ISO 2411 CRE	20.9	KGf/5CM
Flexing Endurance at low temperatures DIN53351 26		
		CYCLES
Resistance to low temperatures DIN53351	-20 °C	°C
Resistance to high temperatures DIN53351	80 °C	°C
Resistance to weathering ASTM G26 Xenon No change 18min spray/2hrs, 100hrs exposure		
Practice for operating light exp With and without water ASTM G26 method A Type B	4	GRADE
Resistance of synthetic polymeric materials to fungi ASTM G21-1996	0	
Fire rating DIN 4102-1	B1	

Roseash Limited, Unit B The Height Business Centre, Ibstone Road, Stokenchurch, Buckinghamshire, HP14 3BG
T: 01494 760240 E : sales@dpm.com W : www.dpm.com