

Technical Data Sheet



Vision Bretta Blackback

Material	33% Polyester / 67% Post-Consumer waste			
Stock widths	app. 320 cm			
Weight				
acc. to DIN EN 12127	260.00	[g/m ²]	+ - 5	[%]
Tearing strength				
Elongation at 100 N, longitudinal direction				
acc. to DIN EN ISO 13934-1	6.00	[%]	+ - 20	[%]
Elongation at 100 N, cross direction				
acc. to DIN EN ISO 13934-1	1.50	[%]	+ - 20	[%]
Maximum tensile elongation, longitudinal direction				
acc. to DIN EN ISO 13934-1	7.00	[%]	+ - 20	[%]
Maximum tensile elongation, cross direction				
acc. to DIN EN ISO 13934-1	45.00	[%]	+ - 20	[%]
Maximum tearing strength, longitudinal direction				
acc. to DIN EN ISO 13934-1	min. 350.00	[N/5 cm]		
Maximum tearing strength, cross direction				
acc. to DIN EN ISO 13934-1	min. 743.00	[N/5 cm]		
Flame Retardancy	B1 / EN13501			



Roseash Limited, Unit B The Height Business Centre, Ibstone Road, Stokenchurch, Buckinghamshire, HP14 3BG
T: 01494 760240 E : sales@dpm.com W : www.dpm.com